

TABLE: ASSAY RESULTS

Hole	Azimuth	Dip	Interval From	Interval To	Interval metres	Estimated True Thickness	Recovery %	Ag (g/T)	Ag (oz/T)	Pb %	Zn %	Sulphide Description
LP267	340	- 63°	155.30	156.10	0.80	0.80	68	880	28.3	6.0	15.3	Massive
LP269	340	- 70°	147.00	150.50	3.50	3.20	100	741	23.8	5.5	26.8	Massive
LP271	0	- 90°	126.05	126.75	0.70	0.70	99	591	19.0	4.4	0.9	Breccia
LP285	330	- 68°	152.40	155.60	3.20	3.00	98	740	23.8	19.9	8.4	Massive
LP288	320	- 60°	164.10	173.95	9.85	8.50	98	677	21.8	9.3	9.2	Massive
LP289	330	- 71°	124.65	129.50	4.85	4.50	100	2,017	64.9	23.9	7.6	Massive
LP290	320	- 66°	150.90	151.80	0.90	0.85	100	1,021	32.8	10.1	10.4	Massive
LP293	310	- 62°	165.60	174.30	7.72	7.00	96	577	18.6	7.8	8.5	Massive
			170.65	174.30	5.14	4.50	96	1,138	36.6	16.4	16.2	Massive
LP298	330	- 76°	123.65	124.30	0.65	0.63	90	5,480	176.2	58.0	1.3	Massive
LP301	270	- 55°	143.15	149.55	6.40	6.00	100	1,351	43.4	14.0	29.9	Massive
			149.55	167.30	17.75	16.00	100					<i>Limestone</i>
			167.30	173.80	6.20	6.00	100	892	28.7	11.3	20.8	Massive
LP302	260	- 60°	137.25	140.59	3.34	2.90	100	1,466	47.1	14.3	29.5	Massive
LP304	235	- 60°	128.70	131.35	2.65	2.30	100	461	14.8	6.2	12.3	Massive